



DISCOUNT STEEL

We've got it!

Melting Points of Metals

Metal or Alloy	Melting Point - °F	Melting Point - °C
Aluminum, pure	1218	658
Brass or Bronze	1600-1660	871-904
Copper	1981	1083
Iron, Cast and Malleable	2300	1260
Lead, pure	620	327
Magnesium	1240	671
Monel	2400	1316
Nickel	2646	1452
Silver, Pure	1762	961
Steel, High Carbon (0.40% to 0.70% carbon)	2500	1371
Steel, Medium Carbon (0.15% to 0.40% carbon carbon)	2700	1482
Steel, Low Carbon (less than 0.15% carbon)	2600	1427
Stainless Steel (18% chromium, 8% nickel)	2550	1399
Titanium	3270	1799
Tungsten	6152	3400
Zinc, Cast or Rolled	786	419

Discount Steel Inc. 216 27th Avenue North, Minneapolis, MN 55411

Phone: (612) 522-5956 • Toll Free: 1-800-522-5950 • Fax: (612) 522-5929 • www.discountsteel.com